

# Intumescent Coating SB (Pyro-kote SB)

Product code: PS3109

## Product Description

**EVI Pyro-kote SB** is a single component solvent based modified acrylic thin film intumescent coating specially designed as a passive fire protection for structural steel against cellulosic fires. The product can be top coated with fire retardant water based coating to give the desired aesthetic look.

## Uses

**Substrates:** Suitably primed carbon steel.

**Area of Use:** Interior and exterior in mildly corrosive environments.

## Specification

<b>Finish</b>	: Matt
<b>Colour</b>	: White
<b>Specific gravity</b>	: $1.38 \pm 0.02$
<b>Solids by Volume</b>	: $65 \pm 2.0$
<b>Diluent</b>	: PT1081XS
<b>Flash point</b>	: 27°C
<b>Spread Rate</b>	: 2 liters per sq. m. at 1.2 mm
<b>Drying Time (30°C at 50RH)</b>	
Dust Free	: 30 minutes
Dry to handle	: 16 hours
Dry to recoat	: 8 hours minimum
<b>Recommended DFT</b>	: 1-1.2 mm

## Surface Preparation

Always ensure that the surface to be painted must be free of dirt, oil and grease. All primers to be coated upon must be completely dried and cured before application of Pyro-kote SB.

## Application Method

Adequate ventilation should always be observed when applying Pyro-kote SB as this is a solvent based product. This will ensure proper drying of the material. Never apply this product in adverse weather conditions such as when the temperature is below 5°C or when the humidity level is above 90%. The surface temperature should always be kept at not less than 3 degree above dew point. In confined spaces constant purging of air during application and drying is necessary to eliminate solvent vapors for reason of health and safety and to assist solvent evaporation.

## Application

The recommended method of application is by airless spray. For hard to reach areas, brush can be used. Clean equipment with PT1081XS before they completely dry.

## Typical Coating System

Product	DFT
EVI Zinc Rich Epoxy	75 microns
EVI Intercoat MIO	150 microns
<b>EVI Pyrokote SB</b>	<b>1200 microns</b>

\* Or as per EVI technical advice.

## Storage & Shelf Life

Under dry and cool condition, Storage stability can be sound up to 18 months in original sealed containers.

## HANDLING

**Disposal:** As per the guidance and legislations of the local Authority e.g., by controlled landfill.

In case of doubt, consult local authority. Do not empty into drains, sewers or other water courses.

**Flash Point:** 27°C

**Caution:** It is strongly advised not to keep open half used drums as it forms a skin on the top layer.

## Safety Precaution

Avoid contact with the skin and eyes. Wear suitable protective clothing such as overalls, goggles, dust mask and gloves. Use a barrier cream. Ensure that there is adequate ventilation in the area where the product is being applied. Do not breathe vapour or spray. MSDS is available on request for the safe handling of this product.

## FIRST AID

**Eyes:** In the event of accidental splashes, flush eyes with warm water immediately and obtain medical advice.

**Skin:** Wash skin thoroughly with soap and water or approved Industrial cleaner. DO NOT USE solvent or thinners.

**Inhalation:** Remove to fresh air, loosen collar and keep patient rested.

**Ingestion:** In case of accidental ingestion DO NOT INDUCE VOMITING. Obtain immediate medical attention.

# Intumescent Coating SB (Pyro-kote SB)

Product code: PS3109

The above Data Sheet is based on our experience and extensive laboratory tests. We guarantee only the quality of the product in this Data Sheet. For safety measurements and details refer to the Safety Data Sheet. Evi reserves the right to modify the contents of the Data Sheet at any time and without prior notice as a system requirement in updating the product.

This Technical Data Sheet surpasses all previously issued versions.

Date Revision : May 03, 2017