

CONCOAT EP250

Solvent Free Epoxy Resin Floor Coating

Composition and Application Field

CONCOAT EP250 is a high performance, two component, solvent free epoxy resin floor coating. The cured film forms a hard coating with excellent adhesion to concrete, granolithic screeds, and certain metal surfaces. **CONCOAT EP250** cures to a glossy, impervious finish which can be easily cleaned. **CONCOAT EP250** is available in a wide range of colors and in clear grade. CONCOAT EP250 complies with British standards BS 476, Part 7: 1971 and BS 5493 -1971.

Advantages

- High impact resistance
- Hard wearing – durable
- Low maintenance costs
- High abrasion resistance
- Provides hygienic – impervious finish
- Primerless
- High chemical resistance
- Applicable to apply on floor and walls

Surface Preparation

All surfaces should be clean, dry and free from dust and other contaminants. Wet substrates should be used sponge dried to remove all surface water, then dried. Treat oil or grease contamination should be removed by degreaser followed by water or steam cleaning. New concrete floors should be at least 28 days and have a moisture content of less than 5%. Excessive laitance should be removed by mechanical method. Dust and other debris should be removed by vacuum cleaning. Old concrete floors damaged areas or surface irregularities should be repaired by using EPOMORTAR FC two component fast curing epoxy mortar (Refer to TDS). Steel surface should be grit blasted then clean by solvent and kept to dry. Epoxy Screeds high spots or trowel marks should be rubbed down and remove dust and debris by vacuum cleaning then repair it by using EPOSCREED 10 three component epoxy screed (Refer to TDS.)

Mixing

The entire contents of the hardener container should be poured into the base container and the two materials mixed thoroughly for at least 3 minutes. Use of heavy duty slow speed power drill with a jiffy mixing blade. Mix the two components in the quantities supplied taking care to ensure hardener container is scraped clean. Do not add solvent thinners at any time.

Application Method

CONCOAT EP250 is recommended to apply in two coats. **CONCOAT EP250** can be applied to prepared surface using airless spray, brush or roller. Ensure that the area is completely coated. If anti-slip finishing is required, broad cast Silica Sand (0.25 – 1.00 mm, at 1 kg/m²) while first coat is wet. Applicator can use spiked shoes and confirm that all area completely covered. The second coat can be applied after 12 to 18 hours at 35 °C.

Coverage

4.5m² /litr at 250 microns (WFT) in two coats.

Cleaning

Tools and equipment can cleaned immediately by using THINNERCOAT 10 organic solvent.

Package

16 litr pack (including colored base and hardener)

Technical Properties

Mixed Density	1.3 + 0.05	
Volume Solids	100 % ± 5	
ASTM D 2823 - 91		
Application Temperature	10°C to 45°C	
Tack Free Time	2 hours at 35°C	
Initial Hardness	20 hours at 35 °C	
Pot Life	30 hours at 35 °C	
Full Cure	7 days at 35°C	
Shore D Hardness	80	
ASTM D 2240 – 91		
Pull – Off (On concrete)	2.5 N/mm ²	
ASTM D 4541 – 85		
Abrasion Resistance	100 cycles 0. 5 -1.0 mg	
(ASTM D 1044-85, CS-17	500 cycles 35 – 45 mg	
Wheel 500 gm load)	1000 cycles < 90 mg	
Flash Point	Non Flammable	
Chemical Resistance:	Gasoline	Resistant
The following chemicals are	Petrol	Resistant
spilled on applied	Diesel	Resistant
samples for 7 days and found	Engine Oil	Resistant
satisfy	Kerosene	Resistant
	NaOH20%	Resistant
	H ₂ SO ₄ 10%	Resistant
	HCl 10%	Resistant
	Acetic 5%	Resistant
	Brake Fluid	Resistant

Storage and Shelf Life

Product should be stored at 25°C in dry conditions. 12 months in tightly closed container.

Flammability

CONCOAT EP250 is nonflammable material. THINNERCOAT 10 so do not expose to naked flames during application..

Health and Safety

The application of material should be in good ventilation and avoid inhalation of the vapors. Use goggles and vinyl gloves. In case of contact with eyes, rinse immediately with plenty of clean water, do not use solvent and seek medical attention immediately. The product complies with environmental and occupational health & safety standards ISO 14001 and OHSAS 18001.